

Product Code AKPEROX A60

Description A mixture of MEKP in Di Methyl Phthalate solution

Specifications;

Density (@20°C) : 1,17 gr/cm³
Viscosity (@20°C) : 25 mPa.s
Appearance : Colorless
Diluent : DMP
Active Oxygen Content : 9,8% - 10,0%
Peroxide Content : 34% - 36%
SADT : 60°C
CAS Nr : 1338-23-4
UN Nr : UN 3105

Applications AKPEROX A60 is a general purpose MEKP for curing unsaturated polyester (UP) resins at room and high temperatures. Suitable for the curing of gelcoat, vinylester resins, button type resins, as well as general purpose resins, dope and casting type polyester resins. Provides earlier gel and cure time than AKPEROX A50. Particularly recommended to be used in GRP Pipe production and general purpose applications.

Usage & Amount It is recommended to use 1% - 2% in general, depending on application. Needs to be used with Cobalt accelerators at room temperature. (E.g. AKCOBALT 1%)

Packaging 30 kgs PE Pail
5 kgs PE Pail
4x5kg in a Carton Box

Handling & Storage Must be kept between +5 C and +30 C. Keep pails tightly closed. Store and handle in a dry, well-ventilated place, away from sources of heat, ignition and direct sunlight in original packaging. Provide grounding and venting in order to prevent static electricity build-up. Avoid any contact with Amine and Cobalt accelerators, acids, alkalis and heavy metal compounds such as driers and metal soaps.

Shelf Life 6 Months
For unopened packages at recommended storage conditions